



HYCON<sup>®</sup>

## Concise Application Sheet

---

### **For reduction clearing of polyester dyeings :**

After polyester dyeing , drain dye bath .

Rinse with fresh water .

Refill water adjust pH with acetic acid to 4

Add

Hycon 1 gpl for Medium shades

1.5 gpl for Dark shades

Raise temperature to 90 C , hold for 10 mins , drain the bath .

Rinse thoroughly with fresh water .

### **For intermediate reduction clearing of polyester-cotton Blends**

#### **One bath reduction clearing and semi bleach for dark and medium shades**

Perform reduction clearing after polyester dyeing as above

With addition of 0.5 gpl Novajet SPL Conc ( Wetting agent ) for better absorbency during cotton dyeing.

This process saves time , water and energy substantially as no neutralization is required as compared to conventional peroxide bleach process.

THE INFORMATION OFFERED IN THIS LEAFLET IS TRUE AND ACCURATE TO THE BEST OF OUR KNOWLEDGE BUT WITHOUT GUARANTEE